



FAIRPRENE® PRODUCT BULLETIN

Fairprene® Code: WFP-N1N1

Description:

Neoprene coated nylon fabric for general purpose application.

Typical Physical Properties:

Base Fabric	Nylon, 1.40 oz.
Polymer Type	CR [Neoprene] 65 Hardness
Typical Gauge	Custom gauges available upon request.
Breaking Strength [grab]	60 x 60 min
Mullen Burst [psi]	140 psi min

General Polymer Characteristics:

		<u>Neoprene/Chloroprene</u>
Solvent Resistance	Aliphatic Hydrocarbons	Good
	Aromatic Hydrocarbons	Fair
	Oxygenated (Ketones, etc.)	Poor
	Lacquer Solvents	Poor
Resistance To	Oil & Gasoline	Good
	Animal & Vegetable Oil	Good
	Water Absorption	Good
	Oxidation	Excellent
	Ozone	Excellent
	Sunlight	Very Good
	Heat Aging	Good to Excellent
	Flame	Very Good
	Heat	Good to Excellent
	Cold	Good

The information supplied herein is based upon information currently available on the subject. This data is based on tests believed to be reliable and consistent with industry practices and is presented in good faith. No warranty or representation including but not limited to merchantability or of fitness for use whether expressed or implied is intended or made, nor is protection from law or patent to be inferred. All rights and patents reserved.



TRELLEBORG

Fairprene® is a registered trade name of Trelleborg Engineered Coated Fabrics
www.TrelleborgECF.com

www.fairprene.com