



FAIRPRENE® PRODUCT BULLETIN: N2RS

Product Code:

WFP-N2RS

[Compare to NS-5550, Neoprene sheet stock]*



Description:

Neoprene sheet stock material with superior quality for highly engineered applications. All Fairprene® materials are manufactured to exact standards and close tolerances.

Typical Physical Properties:

Tensile (psi):	1,850 min. (1,800 typical)	ASTM D-751
Elongation:	350% min.	ASTM D-751
Durometer:	50 Shore A Nominal	
Finish Gauge:	.016", .031", .062", .125" (Custom gauges available upon request)	
Finished Width:	48"	

General Polymer Characteristics:

Resistance To:

- Aliphatic Hydrocarbons
- Aromatic Hydrocarbons
- Oxygenated (Ketones, etc.)
- Lacquer Solvents
- Oil & Gasoline
- Animal & Vegetable Oil
- Water Absorption
- Oxidation
- Ozone
- Sunlight
- Heat Aging
- Flame
- Heat
- Cold

Neoprene (CR)

- Good
- Fair
- Poor
- Poor
- Good
- Good
- Good to Excellent
- Excellent
- Excellent
- Very Good
- Excellent
- Very Good
- Good to Excellent
- Good

The information supplied herein is based upon information currently available on the subject. This data is based on tests believed to be reliable and consistent with industry practices and is presented in good faith. No warranty or representation including but not limited to merchantability or of fitness for use whether expressed or implied is intended or made, nor is protection from law or patent to be inferred. All rights and patents reserved.



TRELLEBORG

*Fairprene® is a registered trade name of Trelleborg Engineered Coated Fabrics
www.TrelleborgECF.com*

www.fairprene.com